QC ABSTRACT

NAME OF WORK: Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeability method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (I.e Chatelier's Method)	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		ReBend test	One Test		1	1
6	Precast (100mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
7	RCC(M20)	Compressive Strength(7days and 28days)	8 set /200-250 cum	212.67	16	16
8	Cement Concrete Pavemet (M30)	Compressive Strength(7days and 28days)	10 set /300-350 cum	313.485	20	20
9	WMM	Sieve Analysis	One Test		1	1
		Impact Value	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1

ಸಿ.ಪಿ.ಪಿ.ಪಿ.ಆ,
ಬೆಂಗಳೂರು

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2020-07-06-08 **Date: 20-04-20**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-04-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	18-04-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.79	–
2	Finess by Air permeablity method (m^2/kg,Min)	295.9	225m^2/kg, Min
3	Density (gm/cc)	3.15	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	145 minutes	Not less than 30 minutes
6	Final Setting time	255 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.0mm	Not more than 10 mm

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE. 14
ಸ.ಕಾ.ಪಾ.ಅ.
ಬಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-07-06-08** **Date: 21-04-20**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	18-04-20
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	18-04-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : **15000 grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	178	178	1.2	98.8	90-100
3	20 mm	7145	7323	48.8	51.2	30-70
4	10 mm	5699	13022	86.8	13.2	10-35
5	4.75 mm	1705	14727	98.2	1.8	0-5
6	Pan	273	15000	100.0	0	---

ಸ.ಆ.ಪಾ.ಆ
ಬಾಗಲಕೋಟೆ

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

TEST REPORT ON COARSE AGGREGATES

Format No: CP/TF/01

Lab ID : **CP-2020-07-06-08**

Date: 21-04-20

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	11.7	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.9	
3	Specific Gravity	2.66	–
4	Bulk Density(Loose) (Kg/l)	1.41	–
5	Bulk Density(Compacted) (Kg/l)	1.47	–
6	Water Absorption(%)	0.24	–

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-07-06-08** **Date: 20-04-20**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-04-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	18-04-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : **5000** **grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	208	208	4.2	95.8	90-100
3	10 mm	2787	2995	59.9	40.1	25-55
4	4.75 mm	1804	4799	96.0	4.0	0-10
5	Pan	201	5000	100	0	–

CIVIL Pro Sig..... Date..... BANGALORE

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-07-06-08** **Date: 20-04-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	9.7	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.5	
3	Specific Gravity	2.63	–
4	Bulk Density(Loose) (Kg/l)	1.45	–
5	Bulk Density(Compacted) (Kg/l)	1.51	–
6	Water Absorption(%)	0.23	–
7	Aggregate crushing Value(%)	23.8	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.7	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸ.ಕಾ.ಪಾ.ಅ,
ಬಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL Pro Sig. Date BANGALORE

End of Report

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : CP-2020-07-06-08 **Date: 20-04-20**

Customer : Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.

Address : T. Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14

Agency : M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010

Customer's Reference : EE/DD/W.O/02/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 18-04-20

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 18-04-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

ಸ. ಕಿ. ಪ್ರಾ. ಪ್ರ.
ಬಾಗಲಗುಂಟೆ

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Date: 20-04-20

Lab ID	:	CP-2020-07-06-08
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-04-20
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	18-04-20
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

ಸ. ಕಾ. ಪ್ರಾ. ಅ.
ಬಾಗೆಗಾಂಡ್

CIVIL PRO Sig Date BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-07-06-08** **Date: 20-04-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸ. ಕಾ. ಪಾ. ಅ.
ಬಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST RESULTS OF STEEL

Date: 06-05-20

Lab ID	:	CP-2020-07-06-08
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-05-20
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	05-05-20

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸ.ಅ.ಎಂ.ಜಾ. ಇ.
ಬಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

Page 1/1
End of Report

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2020-07-06-08** **Date: 20-05-20**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-05-20
Sample Type /Size	:	Precast Cover Slab (100mm)
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	16/05/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.51	100.48	1.116	4477	80.9	18.1	16.8	21.0
2	Cover Slab-2	75.49	100.52	1.122	4475	82.3	18.4	17.1	21.4
3	Cover Slab-3	75.50	100.51	1.118	4476	81.5	18.2	16.9	21.2

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 11/05/2020

Lab ID	:	CP-2020-07-06-08
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-05-20
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	11/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/05/2020	11/05/2020	150.12 X 150.08 X 149.77	22531	8.456	413.5	18.4	18.2
2	Drain Bottom Slab Concrete	M20	04/05/2020	11/05/2020	149.78 X 149.84 X 149.92	22444	8.420	405.5	18.1	
3	Drain Bottom Slab Concrete	M20	04/05/2020	11/05/2020	151.40 X 150.82 X 150.21	22834	8.900	417.3	18.3	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸ.ಕಾ.ಪಾ.ಅ.
ಬಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : CP-2020-07-06-08

Customer : Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore. **Date: 01/06/2020**

Address : T. Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14

Agency : M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010

Customer's Reference : EE/DD/W.O/02/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 06-05-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/05/2020	01/06/2020	151.91 X 151.79 X 149.51	23059	8.494	536.5	23.3	22.9
2	Drain Bottom Slab Concrete	M20	04/05/2020	01/06/2020	149.25 X 149.84 X 150.00	22363	8.004	500.2	22.4	
3	Drain Bottom Slab Concrete	M20	04/05/2020	01/06/2020	149.77 X 150.50 X 151.05	22541	8.616	520.5	23.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಕ. ಕಾ.ಪ್ರ.ಆ.
ವಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2020-07-06-08 **Date: 11/05/2020**

Customer : Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.

Address : T. Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14

Agency : M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010

Customer's Reference : EE/DD/W.O/02/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 06-05-20

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/05/2020	11/05/2020	151.98 X 150.58 X 149.06	22886	8.456	414.7	18.1	18.3
2	Drain Bottom Slab Concrete	M20	04/05/2020	11/05/2020	151.91 X 150.13 X 151.76	22806	8.420	425.2	18.6	
3	Drain Bottom Slab Concrete	M20	04/05/2020	11/05/2020	149.98 X 149.47 X 150.33	22417	8.900	403.8	18.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸ. ಕ್ಷಾ. ಪ್ರ. ಅ.
ಬಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

CIVIL Pro Sig Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	CP-2020-07-06-08 **Date: 01/06/2020**
Customer	:	Assistant Executive Engineer, T. Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T. Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC Roads, Drains and Other Works at Gowdike Hoola (Jodidhar Narasimhaiah Layout) in Ward No.14
Agency	:	M/S Technical Managaer (West), Karnataka Rural Infrastructure Development Limited, No.280, 59th Cross 17th C Main Road, 3rd Y Block Rajaji Nagara, Bangaluru-560010
Customer's Reference	:	EE/DD/W.O/02/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-05-20
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/05/2020	01/06/2020	150.98 X 151.38 X 151.23	22855	8.494	546.3	23.9	23.2
2	Drain Bottom Slab Concrete	M20	04/05/2020	01/06/2020	149.72 X 149.52 X 151.08	22386	8.004	494.4	22.1	
3	Drain Bottom Slab Concrete	M20	04/05/2020	01/06/2020	150.91 X 150.03 X 149.86	22641	8.616	534.4	23.6	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸ.ಇ.ಪಾ.ಅ.
ಬಾಗಲಗುಂಟೆ

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner